


TITLE

**PHOTOCHROMIC DIARYLETHENE SUBSTITUTED WITH  
ISOXAZOLE GROUP**

BACKGROUND OF THE INVENTION

Field of the Invention

- 10 The present invention relates to photochromic diarylethenes substituted with isoxazole group expressed in the following formula (1), which provide excellent dispersability with polymers, especially fluorinated diacrylate monomers capable of photopolymerization and are capable of giving a thin film, prepared therefrom, of superior photochromic characteristic and high mechanical strength with UV
- 15 irradiation to be useful as optical recording material and photo switch,



- wherein R<sup>1</sup> is a direct bond, O, or C<sub>1</sub>-C<sub>3</sub> alkylene optionally substituted with fluoro; R<sup>2</sup> is a hydrogen atom, (CR<sup>4</sup>H)<sub>n</sub>OH or C<sub>6</sub>(R<sup>5</sup>)<sub>m</sub>H<sub>1</sub>; R<sup>3</sup> is selected from the group consisting of a hydrogen atom, phenylisoxazole, hydroxymethylisoxazole, acetyl, hydroxy, and phenyl; R<sup>4</sup> is C<sub>1</sub>-C<sub>10</sub> alkyl; R<sup>5</sup> is chloro, nitro, bromo, or the same as R<sup>4</sup>; X and Y are independently O, N, or S; Z is methylene optionally substituted with fluoro or carbonyl; and n, m and l are an integer of 1 to 5.

#### Related Background Art

- Since 1985, diarylethene compounds have been synthesized and known as
- 10 photochromic compounds having excellent thermal stabilities (Japan Kokai Tokyo Koho; JP 3261781; *J. Org. Chem.*, 1991, 49, 373). Since then, various derivatives have been synthesized and reported for their uses in reversible optical disc, erasable optical disc, photo switch for optical integrated elements, organic photosensitizer, photo-electrode and the like (Japan Kokai Tokyo Koho; JP 789954, JP 8245579;
- 15 Takeshita, M; Uchida, K; Irie, M. Chem. Commun., 1996, 1807-1808).

- Since the diarylethene compounds change their color with UV irradiation and return to the original color with light irradiation having different wavelength, various photochromic compounds are disclosed to be useful in the field requiring
- 20 for colored state and decolored state (Japan Kokai Tokkyo Koho; JP 5222037, JP 5222035, JP 7242659).

- A method for preparing optical recording film by coating with a solution of fluoro-substituted diarylethene compound such as 1,2-bis(2-methylbenzo[b]thiophen-
- 25 3-yl)hexafluorocyclopentene dissolved with polymer resin has been reported because it has high thermal stability and rapid coloring speed (*J. Org. Chem.*, 1991, 49, 373). However, when this fluorinated diarylethene is dissolved into polymer resin, it has problems in preparation of uniform thin film due to poor dispersability and low photochromic effect for low concentration of fluorinated diarylethene in
- 30 the resin. On the other hand, when high concentration of the fluorinated diarylethene is used to increase photochromic effect, prepared thin film may be

unclear and phase separation can be occurred during long storage. Therefore, the conventional photochromic compounds have drawbacks in inferior reliability and storage stability as optical recording materials. Especially, aggregation of conventional diarylethenes results in difficulties in reading and decoding of recorded signals because it gives scattering of data over repeated reversible cycles. In order to solve these problems were disclosed 1-(6'-acetyl-2'-methyl-benzo[b]thiophen-3'-yl)-2-(2"-methyl-benzo[b]thiophen-3"-yl)hexafluorocyclopentene having benzene ring and its derivatives. However, the dispersability is increased some degree but it is hardly regarded as having fully satisfactory sensitivity and photochromic property as photo recording materials (Japan Kokai Tokkyo Koho; JP 05-301873; Irie, M., M. Chem. Rev., 2000, 1685-1716).

### SUMMARY OF THE INVENTION

An object of the present invention is to provide a photochromic diarylethene substituted with isoxazole group which can satisfy the aforementioned requirements with better photochromic effect and dispersability with various polymers such as polyolefins and polycarbonates.

Another object of the present invention is to provide a photochromic thin film composition comprising said diarylethene compounds and a method for preparing thin film.

Further object of the present invention is to provide a composition comprising said diarylethene compounds capable for polymerization and a method for preparing thin film, and more particularly, a photochromic thin film composition comprising fluoro-substituted diacrylate monomer capable of photopolymerization and a method for preparing thin film.

### Brief Description of the Drawings


Fig. 1 illustrates optical change in absorption spectra when light with 365 nm of wavelength is irradiated to the polycarbonate photochromic thin film dispersed with the diarylethene compound according to Example 11 of the present invention.

Fig. 2 illustrates optical change in absorption spectra when light with 365 nm of wavelength is irradiated to the photo-crosslinked acrylate photochromic thin film dispersed with the diarylethene compound according to Example 12 of the present invention.

Fig. 3 illustrates optical change in absorption spectra when light with 365 nm of wavelength is irradiated to the thermally crosslinked acrylate photochromic thin film dispersed with the diarylethene compound according to Example 14 of the present invention.

### Detailed Description of the Invention


The present invention is characterized by photochromic diarylethenes substituted with isoxazole group expressed in the following formula (1),



- wherein  $R^1$  is a direct bond, O, or  $C_1-C_3$  alkylene optionally substituted with fluoro;  
 $R^2$  is a hydrogen atom,  $(CR^4H)_nOH$  or  $C_6(R^5)_mH$ ;  $R^3$  is selected from the group  
 consisting of a hydrogen atom, phenylisoxazole, hydroxymethylisoxazole, acetyl,  
 hydroxy, and phenyl;  $R^4$  is  $C_1-C_{10}$  alkyl;  $R^5$  is chloro, nitro, bromo, or the same as  
 5  $R^4$ ; X and Y are independently O, N, or S; Z is methylene optionally substituted  
 with fluoro or carbonyl; and n, m and l are an integer of 1 to 5.

Said compound (1) is prepared by the following process:

- 10 1) formylation of the diarylethene compound of formula (2);  
 2) sequential reaction with  $NH_2OH \cdot HCl$  and aqueous basic solution and  
 further reaction with N-chlorosuccimide(NCS); and  
 3) reaction with acetylene compound substituted with  $R^2$  in the presence of  
 base catalyst,




- wherein  $R^1$  is a direct bond, O or  $C_1-C_3$  alkylene optionally substituted with fluoro;  
 $R^3$  is selected from the group consisting of a hydrogen atom, phenylisoxazole,  
 20 hydroxymethylisoxazole, acetyl, hydroxy, and phenyl; X and Y are independently  
 O, N, or S; and Z is methylene optionally substituted with a fluoro atom or  
 carbonyl.

- Photochromic compositions containing the diarylethene compound of the present  
 25 invention include photochromic thin film composition and photochromic thin film  
 composition capable of photopolymerization or thermalpolymerization.

Photochromic thin film composition of the present invention comprises 0.1-90wt.% of the compound (1), 10-89.9wt.% of one or more resin selected from the group consisting of polyolefin, polycarbonate, polymethylmethacrylate, polyester, polyvinyl alcohol, polyurethane, and polyimide, and 10-89.9wt.% of one or more solvent.


Photochromic thin film composition capable of photopolymerization or thermalpolymerization of the present invention comprises 0.1-90wt.% of the compound (1), 10-99.8wt.% of fluorinated diacrylate monomer of formula (3), 0-80wt.% of monomer or oligomer having unsaturated group, 0.1-10wt.% of initiator of polymerization selected from initiator of thermalpolymerization and initiator of photopolymerization, and 0-90wt.% of one or more solvent,



wherein n is an integer of 0 to 10.

The diarylethene compound of formula (1) which provides excellent photochromic effect and dispersability with various polymers is prepared by the following method. The preparing method which comprises formylation of diarylethene substituted with R<sup>3</sup> of formula (2), conversion to the corresponding N-oxime and reaction with acetylene compound substituted with R<sup>2</sup> is shown in Scheme 1.

Scheme 1



5

1) Said formulation of the diarylethene compound of formula (2) is carried by the known method (Irie, M.; Miyatake, O.; Uchida, K.; Eriguchi, T., *J. Amer. Chem. Soc.*, **1994**, 9894).

10 2) Said oximization is carried by reacting the reactant dissolved in dimethyl foramide with  $NH_2OH - HCl$  and aqueous basic solution and further reacting with N-chlorosuccinimide(NCS) to yield N-oxime compound.

3) Further reaction is carried by reacting with acetylene compound substituted  
15 with  $R^2$  in the presence of base catalyst in methylene chloride at a temperature of

5

10

15

20

25

The obtained thin film has excellent absorbance in the range of wavelength of 200-500nm. Further, when Sun light or UV light is exposed to the thin film, diarylethene thin film having excellent absorbance in the range of 300-800nm is produced.

5

The diarylethene compound of the present invention provides excellent dispersability with thermalpolymerizable composition or photopolymerizable composition having unsaturated compounds. And further, the diarylethene compound has advantages in excellent dispersability with fluorinated unsaturated monomer, absorbance at 200-800nm, and photochromic effect, so that it can be useful in indicating materials, optical integrated elements, various sensors, recording materials and optical materials.

10

Photochromic thin film composition capable of photopolymerization or thermalpolymerization of the present invention comprises 0.1-90wt.% of one or more selected from the compound (1), 10-99.8wt.% of fluorinated diacrylate monomer of formula (3), 0-80wt.% of monomer or oligomer having unsaturated group, 0.1-10wt.% of one or more polymerization initiator selected from thermalpolymerization initiator or photopolymerization initiator, and 0-90wt.% of one or more solvent. Examples of monomer having unsaturated group include methyl methacrylate, butyl methacrylate, styrene, and  $\alpha$ -methylstyrene. Examples of polymerization initiator include thermalpolymerization initiator such as benzoyl peroxide, 2,2'-azobisisobutyronitrile, and bis(1,1-dimethylethyl)peroxide, and photopolymerization initiator such as 1-hydroxycyclohexyl phenyl ketone, benzophenone, 2-hydroxy-1-[4-(hydroxyethoxy)phenyl]-2-methyl-propanone, 2,2-dimethoxy-2-phenylacetophenone, fluorinated diaryltitanocene, and 2,2-bis(hydroxymethyl)propionic acid. Other additives, used by one having ordinary skill in the art, such as a retardant, a thickener, an antioxidant, and a UV protecting agent may be arbitrarily incorporated, if necessary. The thin film is prepared by molding the composition to yield photochromic forming, coating the photochromic

15

20

25

30

09892655-06004

forming on the substrate such as silicon wafer and glass, and evaporating solvent at 15-130°C or irradiating UV light.

- The compound of formula (1) or photochromic thin film composition is coated on
- 5 the substrate selected from conducting electrode substrate such as aluminum foil, aluminum drum, aluminum plate, platinum, Mylar film, copper plate, conducting glass and conducting plastic; or a substrate such as polypropylene, propylene carbonate, polymethylmethacrylate, polyurethane, plastic, and glass to form diarylethene thin film which can be used for optical recording materials,
- 10 photochromic window, indicating elements, plastic mirror, photochromic filter, photo switch, photosensitive drum, recording elements, solar cell, lens, fiber, or optical elements.

- Although the present invention is described in detail, it is clearly understood that
- 15 the same is by way of illustration and example only and is not to be taken by way of limitation of the scope of the present invention.

**Example 1: Preparation of 1-(6'-oxymoyl-2'-methylbenzo[b]thiophen-3'-yl)-2-(2"- methylbenzo[b]thiophen-3"-yl)hexafluorocyclopentene (OMBTf6)**

- 20 1-(6'-formyl-2'-methylbenzo[b]thiophen-3'-yl)-2-(2"-methylbenzo[b]thiophen-3"-yl)hexafluorocyclopentene (FMBTF6) (3g) was dissolved in 50 mL of ethanol.  $\text{NH}_2\text{OH} \cdot \text{HCl}$  (0.63 g) was added and the mixture solution was stirred for 10 min.  $\text{NaOH}$  (0.36 g) dissolved in 1 mL of water was dropped into the mixture. After the
- 25 reaction was completed, the reaction mixture was extracted with methylene chloride. The combined organic layer was dried over  $\text{MgSO}_4$ , and evaporated *in vacuo* to dryness. The crude product was purified by Flash chromatography (ethylacetate/hexane=1/7) to obtain the desired product, OMBTF6 (2.0g, 65%).

- 30  $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ )  $\delta$  1.73 (s, 1H), 2.21 (s, 3H), 2.49 (s, 3H), 7.17-7.45 (m, 2H), 7.54-7.83 (m, 5H), 8.20 (s, 1H);

MS m/z 511 (M<sup>+</sup>, 100), 493 (18), 478 (5), 464 (26), 419 (10)

**Example 2: Preparation of 1-(6'-chloro-oxymoyl-2',2'-methylbenzo[b]thiophen-3'-yl)-2-(2''-methylbenzo[b]thiophen-3''-yl)hexafluorocyclopentene (COMBTF6)**

OMBTF6(1.3 g) prepared in Example 1 was dissolved in 30 mL of DMF and cooled to 0 °C. N-chlorosuccinimide(0.51 g) was dropped slowly to the reaction mixture. The reaction mixture was left to room temperature and then extracted with methylene chloride. The combined organic layer was washed with NaCl solution, dried over MgSO<sub>4</sub>, and evaporated *in vacuo* to dryness to obtain the product, COMBTF6(1.26 g, 91%).

**Example 3: Preparation of 1-(6'-(5-hydroxymethylisoxazol)-2'-methylbenzo[b]thiophen-3'-yl)-2-(2''-methylbenzo[b]thiophen-3''-yl)hexafluorocyclopentene (IMBTF6)**

CMBTF6(1.26 g) prepared in Example 2 is dissolved in 20 mL of methylene chloride and cooled to 0 °C. Propargyl alcohol (0.26 g) was added and then triethylamine (0.47 g) was dropped slowly to the reaction solution. The reaction mixture was left to room temperature and then extracted with methylene chloride. The combined organic layer was washed with NaCl solution, dried over MgSO<sub>4</sub>, and evaporated *in vacuo* to dryness. The crude product was purified by Flash chromatography (ethylacetate/hexane=1/5) to obtain the product, IMBTF6 (74%).

<sup>1</sup>H NMR (200 MHz, CDCl<sub>3</sub>) δ 1.70 (s, 1H), 2.23 (s, 1H), 2.50 (s, 1H), 4.84 (s, 2H), 6.60 (s, 1H), 7.16-7.41 (m, 2H), 7.50-7.83 (m, 4H), 8.12 (s, 1H);

MS m/z 565 (M<sup>+</sup>, 100), 550 (6), 534 (25), 506 (9), 495 (3)

**Example 4: Preparation of 1-(6'-(5-phenylisoxazol)-2'-methylbenzo[b]thiophen-3'-yl)-2-(2''-methylbenzo[b]thiophen-3'-yl)hexafluorocyclopentene (PIMBTF6)**

- 5 COMBTF6(2.57 g) prepared in Example 3 was dissolved in 40 mL of methylene chloride and cooled to 0 °C. Phenylacetylene (0.96 g) was added and then triethylamine (0.95) was dropped slowly to the reaction solution. The reaction mixture was left to room temperature and then extracted with methylene chloride. The combined organic layer was washed with NaCl solution, dried over  $\text{MgSO}_4$ ,  
10 and evaporated *in vacuo* to dryness. The crude product (85%) was purified by Flash chromatography (ethylacetate/hexane=4/1) to obtain the colorless product, PIMBTF6.

- $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ )  $\delta$  2.24 (s, 3H), 2.52 (s, 3H), 3.07 (s, 1H), 7.19-7.90  
15 (m, 11H), 8.20 (s, 1H);  
MS  $m/z$  611 ( $\text{M}^+$ , 44), 582 (2), 549 (4), 512 (33), 493 (71).

**Example 5 : Preparation of di(6'-phenylisoxazol-2'-methylbenzo[b]thiophen-3'-yl)hexafluorocyclopentene (DPIMBTF6)**

- 20 According to Example 1, di(6'-formyl-2'-methylbenzo[b]thiophen-3'-yl)hexafluorocyclopentene) (3 g) was dissolved in 50 mL of ethanol.  $\text{NH}_2\text{OH} \cdot \text{HCl}$ (1.33 g) was added and stirred for 20 min.  $\text{NaOH}$ (0.7g) dissolved in 2 mL of water was dropped slowly to the reaction mixture. After the reaction was  
25 completed, the reaction mixture was extracted with methylene chloride. The combined organic layer was dried over  $\text{MgSO}_4$ , and evaporated *in vacuo* to dryness. The obtained compound was carried with the same procedure of Examples 2-4 to yield DPIMBTF6 (70%).

- 30  $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ )  $\delta$  1.73 (s, 1H), 2.21 (s, 3H), 2.49 (s, 3H), 7.17-7.45 (m, 2H), 7.54-7.83 (m, 5H), 8.20 (s, 1H).

**Preparation Example 1: Preparation of fluorinated diacrylate monomer (TEBDA)**

To tetrafluoro-1,4-butanediol(1.00 g) dissolved in 50mL of methylene chloride was  
5 dropped triethylamine (1.87 g) dissolved in 10mL of methylene chloride at 6 °C for  
10 min while stirring. Acryloylchloride(1.68 g) dissolved in 10mL of methylene  
chloride was dropped to the reaction mixture for 15 min. The reaction temperature  
was raised to room temperature and stirred for 12 hrs. The reaction mixture was  
washed with saturated NaHCO<sub>3</sub> solution and distilled water (x3), dried over  
10 anhydrous MgSO<sub>4</sub>, and evaporated to yield TFBDA (90%). The crude product was  
purified by column chromatography (ethylacetate/hexane=1:10) to give colorless  
liquid.

IR(KBr) 1174, 1636, 1745, 2973 cm<sup>-1</sup>;  
15 <sup>1</sup>H NMR (CDC1<sub>3</sub>) 4.83 (m, 4H), 6.13-6.73(m, 6H);  
<sup>13</sup>C NMR (CDC1<sub>3</sub>) 59.8, 127.2, 133.2, 164.9;  
MS m/z 270.

**Examples 6 - 7 and Comparative Examples 1 - 4: Preparation of  
20 photochromic thin film composition**

Solubilities of diarylethene compounds of the present invention and known  
diarylethene compounds were compared by dispersing in polycarbonate (PC)  
solution or fluorinated polyethylene.

25 Compared diarylethene compounds are 1-(6'-(5-phenylisoxazol)  
2'-methylbenzo[b]thiophen-3'-yl)-2-(2''-methylbenzo[b]thiophen-  
3'-yl)hexafluorocyclopentene(PIMBTF6) prepared in Example 4 and  
1,2-bis(2-methylbenzo[b]thiophen-3'-yl)hexafluorocyclopentene (BTF6) and  
30 1-(6'-acetyl-2'-methylbenzo[b]thiophen-3'-yl)-2-(2''-methylbenzo[b]thiophen-  
3'-yl)hexafluorocyclopentene (AMBTf6) which are disclosed. Each thin film  
composition was prepared by dissolving 0.03g (10wt.%) of diarylethene compound

and 0.27g (90wt.%) of polycarbonate(PC) or fluorinated polyethylene in a mixture of 1.2g of chloroform and 1.2g of trichloroethylene and stirring at room temperature for 6 hrs. The dispersabilities thereof were summarized in table 1.

5 **Table 1**

Category		Diarylethene compound	Polymer	Solvent	Dispers-ability*
Exam.	6	PIMBTF6	Polycarbonate (PC)	Chloroform + trichloroethylene	O
	7	PIMBTF6	**Fluorinated polyethylene	Chloroform + trichloroethylene	Δ
Comp. Exam.	1	BTF6	Polycarbonate (PC)	Chloroform + trichloroethylene	O
	2	AMBTF6	Polycarbonate (PC)	Chloroform + trichloroethylene	X
	3	BTF6	**Fluorinated polyethylene	Chloroform + trichloroethylene	X
	4	AMBTF6	**Fluorinated polyethylene	Chloroform + trichloroethylene	X
*Dispersability: O = clear solution at RT; Δ = medium solubility; X = insoluble, phase separation and unclear solution					
** Fluorinated polyethylene: Xeonex 480, SamYang Corporation					

**Examples 8 ~ 10 & Comparative Examples 5 ~ 9: Preparation of photochromic thin film composition capable of polymerization**

Solubilities of diarylethene compounds of the present invention and known diarylethene compounds were compared by dispersing in fluorinated diacrylate monomer (TFBDA) or THF.

The same diarylethene compounds used in Examples 6-7 and Comparative Examples 1-4 are used to obtain the desired composition. Each thin film composition was prepared by dissolving 0.01g (10wt.%) of diarylethene compound and 0.002g (2wt.%) of 1-hydroxycyclohexyl phenyl ketone as photopolymerization

initiator in 0.088g (88wt.%) of TFBDA and stirring at room temperature for 30 min. The dispersabilities thereof were summarized in table 2.

**Table 2**

Category		Diarylethene compound	Solvent	Dispersability*
Exam.	8	PIMBTF6	TFBDA	O
	9	DPIMBTF6	TFBDA	O
	10	PIMBTF6	THF	O
Comp. Exam.	5	BTF6	TFBDA	X
	6	AMBTF6	TFBDA	Δ
	7	IMBTF6	TFBDA	X
	8	AMBTF6	THF	O
	9	IMBTF6	THF	O
*Dispersability: O = clear solution at RT; Δ = medium solubility; X = insoluble, phase separation and unclear solution				

**Example 11: Preparation of thin film using photochromic thin film composition**

- 20 The photochromic composition obtained in Example 6 was filtered through 0.45 micron filter of syringe and filtrate was coated on the surface of glass by using bar code. The coated glass was dried in the vacuum oven at 50°C for 12 hrs to yield transparent thin film having excellent adhesive and high strength. When the obtained thin film was irradiated with light of over 300nm, the color was changed
- 25 to red and then kept in the dark room to remain red color. Fig. 1 illustrates changes of absorption spectra when light with 365 nm of wavelength is irradiated to the photochromic thin film dispersed with the PIMBTF6, wherein a broken line is

absorption spectra prior to light irradiation and a solid line is absorption spectra after 5 min from light irradiation.

5 **Comparative Examples 10-11: Preparation of thin film using photochromic thin film composition**

Photochromic thin films of Comparative Examples 10 and 11 were prepared by using the compositions prepared in Comparative Examples 1 and 2 according to Example 11.

10

**Examples 12-13: Preparation of thin film using photochromic thin film composition capable of polymerization (photocuring)**

15 The photochromic compositions obtained in Examples 8 and 9 were filtered through 0.45 micron filter of syringe. Filtrate was injected in between glasses and exposed with UV light for 10 min. One of glasses was removed to yield transparent thin film having excellent adhesive and high strength. When the obtained thin film was irradiated with light of over 300nm, the color was changed to red and then kept in the dark room to remain red color. Fig. 2 illustrates changes of absorption spectra when light with 365 nm of wavelength is irradiated to the photochromic thin film of Example 12, wherein a broken line is absorption spectra prior to light irradiation and a solid line is absorption spectra after 5 min from light irradiation.

25 **Comparative Example 12: Preparation of thin film using photochromic thin film composition capable of polymerization (photocuring)**

Photochromic thin film was prepared by using the composition prepared in Comparative Examples 6, according to Example 12.

**Examples 14-15: Preparation of thin film using photochromic thin film composition capable of polymerization (thermal curing)**

- 5 The thin films were prepared according to Example 12 except with thermal curing at 80°C instead of radiation curing. When the obtained thin film was irradiated with light of over 300nm, the color was changed to red and then kept in the dark room to remain red color. Fig. 3 illustrates changes of absorption spectra when light with 365 nm of wavelength is irradiated to the photochromic thin film of Example 14, wherein a broken line is absorption spectra prior to light irradiation
- 10 and a solid line is absorption spectra after 5 min from light irradiation.

**Comparative Example 13: Preparation of thin film using photochromic thin film composition capable of polymerization (thermal curing)**



- 15 Photochromic thin film was prepared by using the composition prepared in Comparative Examples 6, according to Example 14.

**Experimental Example 1: Comparison of photochromic characteristics of thin films prepared with photochromic thin film compositions**

20

Photochromic characteristics of the thin films prepared in Example 11 and Comparative Examples 10-11 were summarized in table 3.




**Table 3**

Category		Photochromic composition	Substituent of diarylethene		Content (wt %)	Thickness of film (μm)	$\lambda_{max}$	$\Delta OD^*$ (cm <sup>-1</sup> )
Exam.	10	Exam. 6	-H		10	5	540	235
Comp. Exam.	11	Comp. Exam. 1	-H	-H	10	3	526	148
	11	Comp. Exam. 2	-H		10	5	539	174
Δ OD* is an amended value with the thickness of thin film for the difference between absorbance of $\lambda_{max}$ before and after UV irradiation								




**Experimental Example 2: Comparison of photochromic characteristics of thin films prepared with photochromic thin film compositions capable of polymerization**

Photochromic characteristics of the thin films prepared in Examples 12-14 and Comparative Examples 12-13 were summarized in table 4.

**Table 4**

Category		Photochromic composition	Substituent of diarylethene		Content (wt %)	Thickness of film (μm)	$\lambda_{max}$	$\Delta OD^*$ (cm <sup>-1</sup> )
Exam	12	Exam. 8	-H		10	12	539	259
	13	Exam. 9			10	15	545	280

5

Comp. Exam.	12	Comp. Exam. 6	-H		10	18	533	231
Exam.	14	Exam. 8	-H		10	17	538	185
Comp. Exam	13	Comp Exam 6	-H		10	12	540	180
Δ OD* is an amended value with the thickness of thin film for the difference between absorbance of λ <sub>max</sub> before and after UV irradiation								

- 10 As shown in Experimental Examples 1 and 2, the compositions of Examples 11-14 containing photochromic diarylethene compound PIMBTF6 provide superior photochromic effect to that of Comparative Example 1 containing BTF6 and Comparative Examples 2 and 6 containing AMBTF6. And further, photochromic effect was generally better with fluorinated diacrylate substrate than that with
- 15 polycarbonate substrate.

Accordingly, diarylethene compounds having isoxazole group of the present invention provide excellent dispersability with polymers, especially fluorinated diacrylate monomer capable of photopolymerization, and photochromic effect, so

20 that such compounds or composition containing the same can be highly useful in the preparation of optical recording materials, photo switch, photosensitive drum, recording elements, fiber and optical elements.